


TECHNICAL DATA SHEET

BIANCO CARRARA C - C/D



Primary name	Bianco Carrara C - C/D
Type of stone	Marble
Country of origin	Italy
Quarry location	Carrara (MS) - Tuscany
Geological formation	Jurassic
Color range	White - Grey
Description	Thin veins from grey to black on a white background. The transition between the qualities known as "C" and "CD" is distinguished by a gradual increase in the veining and a grayer background. Particularly appreciated for its fine grain.
Average Block size	250 x 120 x 120 cm
Average Fabricated Slab size	250 x 120 cm
Available in Thin Tile	Yes
Maximum Thin Tile size	61 x 61 x 1 cm

TECHNICAL INFORMATION	ENGLISH VALUE	ASTM ** Test Method
Absorption by weight, %	0.1	C97
Density, lbs/ft ³ , (kg/m ³)	169.41	C97
Compressive strenght, psi, (MPa)	10,930	C170
Abrasion resistance, hardness	14.24	C241
Flexural strength, psi, (MPa)	2,799	C880

Natural stone is an easy solution to many green building goals. It is nearly complete as a building material in its natural state as mother nature does most of the manufacturing. It is a single-ingredient natural material that emits no VOCs. Its durability allows stone to perform impeccably in commercial & residential applications.

MIA Classification for Soundness A (Marble Only) - Other trade names / - Color plate and information supplied by: Marmi e Graniti d'Italia Sicilmarmi Spa, Massa, Italy

Technical details provide a frame of reference only. Because stone is a product of nature, testing to determine specific physical should be repeated for each major project. Control Number II - 01

** American Society for Testing and Materials; standards developed by Committee C18

© Copyright 1993, DIMENSION STONES OF THE WORLD © - Volume II; Marble Institute of America printed in U.S.A

Marmi e Graniti d'Italia Srl Via Aurelia Ovest, 271 - 54100 - Massa (MS) - Italy - www.marmiegraniti.it